

TEST CERTIFICATE

DATE SUBMITTED: 09-MAY-2017
DATE ISSUED: 10-MAY-2017
REPORT NO: 42651
COMPANY ORDER NUMBER: 60625

CUSTOMER CONTACT NAME: REBECCA GRIMES
TEL: 01924 481 366
EMAIL: rebecca.grimes@carmirafabrics.com

COMPANY: CAMIRA FABRICS LTD
MELTHAM MILLS
MELTHAM
WEST YORKSHIRE
HD9 4AY

CUSTOMER SAMPLE DESCRIPTION

FIBRE COMPOSITION: Not Stated
SAMPLE QUALITY/BATCH: Quality: Aquarius Zirpro RUN: 310920
SAMPLE DESCRIPTION: Aquarius Zirpro
SAMPLE COLOUR: Lt Taupe
SAMPLE END USE: Contract and Transport Uphostery
FABRIC CUSTOMER: Not Stated
FABRIC SUPPLIER: Camira Fabrics

FIRE TEST REQUESTED:
(Confidential Report)

BS 5867: 2008 Part 2 Type B Flammability requirements (fabrics for curtains, drapes and window blinds) in accordance with BS EN ISO 15025:2002 Procedure A (surface ignition). Protective clothing – Protection against heat and flame – Method of test for limited flame spread.

LAUNDERING PROCEDURE:

Sample was tested as received after the appropriate conditioning requirements

WARNING: IF WETTED IN ANY WAY IT IS ESSENTIAL TO RE-TREAT THE FABRIC TO MEET FLAMMABILITY REQUIREMENTS

CONDITIONING PRIOR TO TESTING:

The sample specimens were conditioned immediately prior to testing for @ least 24 h at 65 +/- 5% r h and 20 +/- 2 °C

Authorised signature:

Signed:  v

Zeb Alam
Technical Manager

DATE SUBMITTED: 09-MAY-2017
 DATE ISSUED: 10-MAY-2017
 REPORT NO: 42651
 COMPANY ORDER NUMBER: 60625

PROCEDURE:

The specimens were tested directly after the appropriate conditioning requirements (as stated on page one), three samples were tested in the length (warp) direction & three in the width (weft) direction using a flame application time of 15 seconds in accordance with Type B

REQUIREMENTS:

Type B: No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen and there shall be no separation of any flaming debris from any specimen.

DATE OF TEST: 10-May-2017

RESULTS:

The test results may not apply in situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Specimen Reference	Orientation of test specimen					
	Fabric length direction			Fabric width direction		
Face tested						
Specimen designation	1	2	3	4	5	6
	↑	↓	↑	→	←	→
Application time (s)	15	15	15	15	15	15
Hole formed (Y/N)	Yes	Yes	Yes	Yes	Yes	Yes
Hole reached edge (Y/N)	No	No	No	No	No	No
Flame reached edge (Y/N)	No	No	No	No	No	No
Flaming debris (Y/N)	No	No	No	No	No	No
Damage length mm	24	27	28	30	28	30
Damage width mm	56	58	64	57	56	61
Result	Pass	Pass	Pass	Pass	Pass	Pass

CONCLUSION

Flammability **complies** with the requirements of BS5867-2: 2008 type B

RESULT: PASS